



**TRGOVINA IN STORITVE D.O.O.**  
Cesta na Fužine 2, 8233 Mirna  
Slovenija, EU  
T: +386 41 358 251  
F: +386 73 047 149  
E: info@prodel.si

# PROTAN G

## PYROCATECH TANNIN

### ANALYSES

TANNINS	43% +/- 5
NON TANNINS	29% +/- 5
pH SOLUTION 1:10	3.7 - 5.7

### PROPERTIES AND APPLICATIONS

PROTAN G is a pyrocatechuic tannin, modified to obtain greater penetration.

The main characteristics of this tannin are that it has greater uniformity, a better dispersing effect on dyes, greater softness and less swelling.

Thanks to its particular chemical composition, PROTAN G does not react with mineral salts.

PROTAN G is particularly recommended in the retanning of chrome leathers, if you want to obtain leathers with a softer and softer hand, as well as improving the buffing.

Thanks to its pasty and swelling power, PROTAN G is particularly indicated for retanning leather that is too flat and firm after tanning.

### METHOD OF USE

In retanning of chrome leathers 5 - 10% on shaved weight depending on the item requested.